


TEST REPORT

Lightwater Quarries Ltd
Potgate Quarry
North Stainley
Ripon
HG4 3JN



White
Rose
Laboratory
Services
Ltd

Lumley St • Castleford • WF10 5LB
01977 520625 • enquiries@whiteroselabs.co.uk

Report WRL/18/0693la
Issue date 11/04/18

Material	40mm Crusher Run (Crushed Limestone)		
Site	Gebdykes Quarry		
Specification	-	Sample N°	S/18/0693
Source	Gebdykes Quarry	Sampled by	M O'Hara/A Mason
Supplier	Lightwater Quarries Ltd	Date sampled	06/04/18
Sample location	Stockpile	Date received	06/04/18
Sample type	Bulk	Date tested	09/04/18
Order number	8815LQ	Date reported	11/04/18

BS EN 1097-2 2010 Los Angeles Coefficient

Test portion was obtained from the 10 - 11.2mm and 11.2 - 14mm fractions.

LA coefficient 36

A handwritten signature in black ink, appearing to read 'M Randerson'.

M Randerson
Laboratory Services Director